

FIXER

SBS Torch On Roofing System



- Available in 4 colours
- Polyester
- Top Sheet, Capsheet and Underlayers
- Guaranteed 15 Years*

Introduction The FIX-R SBS Torch On Roofing System is intended as a torch-applied built up roofing system for flat and pitched roofs. FIX-R SBS membranes are ideal for new roofs and the repair of existing felt and asphalt roofs.

Description The FIX-R SBS Torch On Roofing System consists of reinforced bitumen membranes using polyester reinforcements with exceptional mechanical strength and dimensional stability. The reinforcements are impregnated and then coated with specially formulated SBS (Styrene Butadiene Styrene) modified bitumen.

FIX-R SBS Capsheets consist of a polyester carrier coated with SBS rubber modified bitumen. The upper surface is finished with a factory applied choice of green, brown, blue-grey or black mineral granules and the lower surface has a sacrificial film which rapidly melts during the torching operation. A 90mm sacrificial film selvedge facilitates bonding of side laps.

FIX-R Top Layer consists of a polyester carrier coated with SBS rubber modified bitumen. The upper surface is finished with fine sand and the lower surface has a sacrificial film which rapidly melts during the torching operation.

*When FIX-R Capsheet is used in conjunction with FIX-R Underlay.

Other System Products

FIX-R Torch On Universal Underlay consists of a glass tissue carrier coated with rapid flow rubber modified bitumen. The upper surface is finished with fine sand and the lower surface has a sacrificial film which rapidly melts during the torching operation.

FIX-R Universal Torch On Venting Layer is a product with 40 mm perforations specially designed for torch on systems, where partial bonding of the underlayer is required.

Nominal Dimensions and Weights

	Guarantee*	Product Code	Roll Length/Width	Finish	Roll Weight	Weight m ²
FIX-R SBS Sanded Top Layer	15 years	119100030/ 10205571	8 x 1 m	Sand	36.0 kg	4.5 kg/m ²
FIX-R SBS Capsheet	15 years	119100010/ 10205567	8 x 1 m	Green Mineral	38.0 kg	4.75 kg/m ²
FIX-R SBS Capsheet	15 years	119100025/ 10205570	8 x 1 m	Blue-grey Mineral	38.0 kg	4.75 kg/m ²
FIX-R SBS Capsheet	15 years	119100015/ /10205568	8 x 1 m	Brown Mineral	38.0 kg	4.75 kg/m ²
FIX-R SBS Capsheet	15 years	119100020/ 10205569	8 x 1 m	Black Mineral	38.0 kg	4.75 kg/m ²
FIX-R Universal Underlay	15 years	119100005/ 10205566	16 x 1 m	Sand	36.0 kg	2.25 kg/m ²
FIX-R Universal Torch On Venting Layer	-	119100065/ 10205578	20 x 1 m	Sand	28.0 kg	1.4 kg/m ²

* Build up must be installed in accordance with the British Standards Code of Practice.

* When FIX-R Capsheet is used in conjunction with FIX-R Underlay.

Performance Benefits

- Tough polyester reinforcement for membrane strength and durability.
- Remains flexible at temperatures lower than -10°C.
- Excellent adhesion facilitates all detailing work.
- High resistance to puncture.
- Rapid melt sacrificial backing speeds torching application.
- Compatible with Marley Waterproofing high performance elastomeric pour and roll systems.
- Range of 4 mineral colours.

Uses

FIX-R SBS Membranes are designed to be torch applied to most recommended roof decks as part of a complete roofing specification.

They must not be directly torched to combustible sub-structures.

FIX-R SBS Capsheet is used as the external layer of the system and is also suitable for forming upstands and all detailing work.

FIX-R SBS Sanded Top Layer can be used as the external layer of the system but it must always be protected with mineral chippings, promenade tiles or other suitable protective finish.

FIX-R Universal Underlay is designed for use installed beneath the Top Layer or Capsheets.

Technical Characteristics

The following table gives typical values for FIX-R SBS Capsheet.

Characteristic	Method	Units	FIX-R SBS Capsheet
Tensile strength	EN 12311	N/50mm	810/630
Elongation at peak load	EN 12311	%	29/28
Resistance to tearing	EN 12310	N	210/210
Resistance to static loading	EN 12730(B)	kg	20
Flexibility at low temperature	EN 1109	°C	< - 10
Watertightness at 10 kPa	EN 1928		PASS
External Fire Performance	EN 13501-5		F _{ROOF} (t4)

BS 8747 Classification

FIX-R SBS Capsheet and Top Layer achieve **Performance Class S4** as described in BS 8747: 2007.

Application

Storage

FIX-R SBS membranes must be stored on end, on a clean, level surface away from excessive heat and under cover.

Preparation

The surface over which FIX-R SBS membranes are to be installed should be clean and dry and the deck must comply with the relevant requirements of BS 6229:2003. If a primer is necessary, this must be allowed to dry completely. Porous or very dusty /friable surfaces may require a second coat of bitumen primer.

Installation

Normal good practice must be followed and be generally in accordance with BS 8217.

Protection

In compliance with good roofing practice, completed work should be protected from damage, particularly if following trades will be working on or over the roof.

Site Quality Control

Regular inspection of the work in progress should be made to ensure that the work is executed to a good standard and in accordance with the specification.

Site Safety

Guidance given in BS 8000: 1989 and the CDM Regulations: 2007 should be followed. Provision should be made for adequate scaffolding to ensure the safety of operators in accordance with health and safety requirements.

The logo for FIX-R, featuring the word 'FIX-R' in a bold, black, sans-serif font with a yellow outline, set against a white background.

Harding Way,
St Ives,
Cambridgeshire,
PE27 3YJ

Tel: 01480 466777
Fax: 01480 290133

Email:
info@fix-r.co.uk